

**PREPARATION AND CHARACTERIZATION OF A CARRIER
SYSTEM FOR α -TOCOPHEROL FROM HEN EGG WHITE
PROTEIN/ AND OBSERVATION OF α -TOCOPHEROL-
INDUCED GOLD NANOPARTICLES GROWTH USING
FLOW FIELD-FLOW FRACTIONATION**



**A THESIS SUBMITTED IN PARTIAL FULFILLMENT
OF THE REQUIREMENTS FOR
THE DEGREE OF MASTER OF SCIENCE
(APPLIED ANALYTICAL AND INORGANIC CHEMISTRY)
FACULTY OF GRADUATE STUDIES
MAHIDOL UNIVERSITY
2009**

COPYRIGHT OF MAHIDOL UNIVERSITY

PREPARATION AND CHARACTERIZATION OF A CARRIER SYSTEM FOR α -TOCOPHEROL FROM HEN EGG WHITE PROTEIN/ AND OBSERVATION OF α -TOCOPHEROL-INDUCED GOLD NANOPARTICLES GROWTH USING FLOW FIELD-FLOW FRACTIONATION

WIMUT SERMSRI 4936461 SCAI/M

M.Sc. (APPLIED ANALYTICAL AND INORGANIC CHEMISTRY)

THESIS ADVISORY COMMITTEE: ATITAYA SIRIPINYANOND, Ph.D. (ANALYTICAL CHEMISTRY), JUWADEE SHIOWATANA, Ph.D. (ANALYTICAL CHEMISTRY)

ABSTRACT

Hen egg white protein (HEW) was examined for its ability to encapsulate α -tocopherol after salt-induced gelation of protein. Parameters affecting encapsulation efficiency were investigated including protein, α -tocopherol, and salt (ZnCl_2) concentrations. Concentrations of protein, α -tocopherol, and ZnCl_2 were shown to have an influence on encapsulation efficiency. The optimum condition of HEW-encapsulated α -tocopherol was as follows: HEW of 4.0% (w/v), α -tocopherol of 50 mM, and ZnCl_2 of 25 mM. With this condition, encapsulation efficiency by HEW was approx. 32%. From the *in vitro* estimation, the release of α -tocopherol was nearly 100% in simulated gastric condition. Alginate was therefore used for the coating of these encapsulated particles to prolong the release of α -tocopherol till simulated intestinal condition. With the optimum alginate concentration of 0.25% (w/v), the α -tocopherol of approx. 38% were retained and released in the simulated intestinal condition from HEW-encapsulated particles.

The effect of α -tocopherol on the enlargement of gold nanoparticles (GNPs) was observed. Gold nanoparticles were prepared by mixing AuCl_4^- (1×10^{-3} M) with FL-70 (0.01%) and sodium citrate (2×10^{-4} M) in phosphate buffer (pH 8.0; 1×10^{-2} M) with various concentrations of α -tocopherol. All samples were heated at 45 °C for 10 min. Flow field-flow fractionation (FIFFF) was applied to observe the growth of gold nanoparticles (GNPs)-induced by α -tocopherol. Parameters affecting growth of GNPs were investigated including α -tocopherol and incubation time. Larger particle sizes of GNPs were formed with increasing in α -tocopherol and incubation time.

KEY WORDS: HEN EGG WHITE PROTEIN/ α -TOCOPHEROL/ ALGINATE/ GOLD NANOPARTICLES/ FLOW FIELD-FLOW FRACTIONATION

92 pages

การเตรียมและการทดสอบคุณลักษณะอนุภาคนำส่งสำหรับแอลฟา-โทโคฟีรอลจากโปรตีนไข่ขาว/ และ การสังเกตแอลฟา-โทโคฟีรอลในการเหนี่ยวนำการขยายขนาดของอนุภาคทองขนาดนาโนเมตร โดยใช้เทคนิคการแยกแบบไหลภายใต้สนามโดยอาศัยแรงไหล

PREPARATION AND CHARACTERIZATION OF A CARRIER SYSTEM FOR α -TOCOPHEROL FROM HEN EGG WHITE PROTEIN/ AND OBSERVATION OF α -TOCOPHEROL-INDUCED GOLD NANOPARTICLES GROWTH USING FLOW FIELD-FLOW FRACTIONATION

วิมุติ เสริมศรี 4936461 SCAI/M

วท.ม. (เคมีวิเคราะห์และเคมีอินทรีย์ประยุกต์)

คณะกรรมการที่ปรึกษาวิทยานิพนธ์: อติยา ศรีภิญโญนนท์, Ph.D. (ANALYTICAL CHEMISTRY),
ยุวดี เชื้อววัฒน์, Ph.D. (ANALYTICAL CHEMISTRY)

บทคัดย่อ

ได้ทดสอบความสามารถในการห่อหุ้มแอลฟา-โทโคฟีรอลของโปรตีนไข่ขาว (HEW) หลังจากการทำให้โปรตีนเป็นเจลโดยการเหนี่ยวนำด้วยเกลือ ตรวจสอบตัวแปรที่มีผลต่อประสิทธิภาพการห่อหุ้ม ประกอบด้วย ความเข้มข้นของโปรตีน ความเข้มข้นของแอลฟา-โทโคฟีรอล, และความเข้มข้นของเกลือ ($ZnCl_2$) สภาวะที่เหมาะสมของแอลฟาโทโคฟีรอลที่ถูกห่อหุ้มด้วยโปรตีนไข่ขาวเป็นดังนี้ HEW 4.0% (น้ำหนัก/ปริมาตร) แอลฟา-โทโคฟีรอล 50 mM และ $ZnCl_2$ 25 mM โดยในสภาวะนี้ ประสิทธิภาพการห่อหุ้มด้วย HEW มีค่าประมาณ 32% จากการประเมินค่าในสภาวะที่จำลองขึ้น การปลดปล่อยของแอลฟา-โทโคฟีรอลมีค่าใกล้เคียง 100% ในสภาวะกระเพาะจำลอง ดังนั้นจึงได้ใช้แอลจินเทคัลลอสอนุภาคที่ถูกห่อหุ้มนี้เพื่อยืดเวลาการปลดปล่อยของแอลฟา-โทโคฟีรอลให้เกิดที่สภาวะลำไส้จำลอง ด้วยความเข้มข้นแอลจินเทคัลลอสที่เหมาะสม 0.25% (น้ำหนัก/ปริมาตร) แอลฟา-โทโคฟีรอลประมาณ 38% ยังคงอยู่และถูกปลดปล่อยจากอนุภาคที่ถูกห่อหุ้มด้วยHEWในสภาวะลำไส้จำลอง

ได้สังเกตอิทธิพลของแอลฟา-โทโคฟีรอลที่มีต่อการขยายขนาดของอนุภาคทองขนาดนาโนเมตร (GNPs) GNPs เตรียมโดยผสม $AuCl_4^-$ (1×10^{-3} M) กับ FL-70 (0.01%) และ sodium citrate (2×10^{-4} M) ในสารละลายฟอสเฟตบัฟเฟอร์ (pH 8.0; 1×10^{-2} M) ด้วยความเข้มข้นของแอลฟา-โทโคฟีรอลที่แตกต่างกัน ทุกตัวอย่างได้ให้ความร้อนที่ 45 °C เป็นเวลา 10 นาที ได้ประยุกต์ใช้เทคนิคการแยกภายใต้สนามแบบไหลเพื่อสังเกตการขยายขนาดของ GNPs ที่ถูกเหนี่ยวนำด้วยแอลฟา-โทโคฟีรอลตรวจสอบตัวแปรที่มีผลต่อการเติบโตของ GNPs ประกอบด้วย แอลฟา-โทโคฟีรอลและเวลา ซึ่งพบว่า GNPs มีขนาดใหญ่ขึ้นเมื่อแอลฟา-โทโคฟีรอลและเวลาเพิ่มขึ้น