



**CHEMICALLY MODIFIED KEVLAR FIBRE-THERMOPLASTIC  
ELASTOMER COMPOSITES : MECHANICAL PROPERTIES  
AND MORPHOLOGY**

**SUNAN SAIKRASUN**

**With compliments  
of**

ปัทมาภรณ์ พล. ๒๕๖๓

**A THESIS SUBMITTED IN PARTIAL FULFILLMENTS  
OF THE REQUIREMENTS FOR  
THE DEGREE OF MASTER OF SCIENCE  
(PHYSICAL CHEMISTRY)**

**FACULTY OF GRADUATE STUDIES**

**MAHIDOL UNIVERSITY**

**1998**

**ISBN 974-661-414-2**

**COPYRIGHT OF MAHIDOL UNIVERSITY**

3937570 SCPC/M : MAJOR : PHYSICAL CHEMISTRY ; M.Sc. (PHYSICAL CHEMISTRY)

KEY WORD : KEVLAR FIBRE / THERMOPLASTIC ELASTOMER

SUNAN SAIKRASUN : CHEMICALLY MODIFIED KEVLAR FIBRE-THERMOPLASTIC ELASTOMER COMPOSITES : MECHANICAL PROPERTIES AND MORPHOLOGY. THESIS ADVISOR : SAUVAROP LIMCHAROEN, Dr.rer.nat., TAWEECHAI AMORNSAKCHAI, Ph.D., CHAKRIT SIRISINHA, Ph.D. 132 p. ISBN 974-661-414-2

This study consists of two parts. In the first part, reinforcement of styrene (butylene ethylene) styrene thermoplastic elastomer (SEBS) with Kevlar fibre was investigated. Surface treatment of the fibre was carried out by N-alkylation to introduce the non-polar groups on the polar fibre surface. The effect of N-alkylation on surface morphology of Kevlar fibre was investigated by Scanning Electron Microscopy. Diffuse reflectance FT-IR (DRIFT) and solid state NMR techniques were used to characterise the surface of Kevlar fibre before and after N-alkylation. After N-alkylation, Kevlar fibre surface shows high degree of surface roughening and fibrillation. Mixing conditions for the preparation of Kevlar-SEBS composites in an internal mixer were at 165°C with a rotor speed of 90 rpm. It was found that increasing the amount of untreated fibre caused an increase in modulus, but decreases in tensile strength and elongation at break. After N-alkylation on fibre surface, a slight decreases in modulus and elongation at break of the composite were observed, but tensile strength was increased. Pulp was found to give composites with better mechanical properties than the short fibre.

In the second part, reinforcement of Santoprene thermoplastic elastomer with Kevlar pulp was investigated. Surface treatment of the fibre was carried out by alkali hydrolysis to increase the number of the reactive end groups. The effect of hydrolysis on surface morphology of Kevlar pulp was investigated by Scanning Electron Microscopy. DRIFT technique was used to characterise the surface of Kevlar fibre before and after hydrolysis. After hydrolysis, no significant change on Kevlar fibre surface was observed. Mixing conditions for the preparation of Kevlar pulp-Santoprene composites in an internal mixer which give the highest value of tensile properties were found to be at 175°C with a rotor speed of 90 rpm. It was found that increasing the amount of fibre resulted in increases of modulus and tensile strength, but a decrease in elongation at break. Addition of MA-g-PP as a compatibiliser to the composites of hydrolysed Kevlar pulp-Santoprene was found to improve the mechanical properties of the composite significantly. Hence, surface hydrolysis of Kevlar was found to be necessary for MA-g-PP, which produces a composite with significantly improved properties, to function.

3937570 SCPC/M : สาขาวิชา : ฟิสิกส์เคมี; วท.ม. (ฟิสิกส์เคมี)

ผู้แต่ง : สายกระสุน : คอมโพสิตระหว่างเส้นใยเคฟลาร์ที่ผ่านกระบวนการทางเคมีกับยางเทอร์โมพลาสติก : สมบัติเชิงกลและลักษณะโครงสร้างพื้นฐาน (CHEMICALLY MODIFIED KEVLAR FIBRE-THERMOPLASTIC ELASTOMER COMPOSITES : MECHANICAL PROPERTIES AND MORPHOLOGY) คณะกรรมการควบคุมวิทยานิพนธ์ : เสาวรภย์ ลิมเจริญ Dr.rer.nat., ทวีชัย อมรศักดิ์ชัย Ph.D., ชาคริต สิริสิงห Ph.D. 132 หน้า. ISBN 974-661-414-2

งานวิจัยนี้แบ่งเป็น 2 ส่วน ส่วนแรกเป็นการศึกษาการเสริมแรง styrene (ethylene butylene) styrene (SEBS) เทอร์โมพลาสติก อีลาสโตเมอร์ ด้วยเส้นใยเคฟลาร์ โดยนำเส้นใยไปทำปฏิกิริยา N-alkylation ที่ผิวของเส้นใย ซึ่งได้ทำการศึกษาผลของปฏิกิริยา N-alkylation โดยใช้อินฟราเรดสเปกโตรสโกปี นิวเคลียร์แมกเนติกเรโซแนนซ์สเปกโตรสโกปี และกล้องจุลทรรศน์อิเล็กตรอน หลังจากทำปฏิกิริยา พบว่าที่ผิวเส้นใยมีความขรุขระมากขึ้นและเกิด fibrillation คอมโพสิตระหว่างเส้นใยเคฟลาร์กับ SEBS ซึ่งเตรียมโดยใช้เครื่องผสมระบบปิดที่อุณหภูมิ 165 องศาเซลเซียส และความเร็วของโรเตอร์ 90 รอบต่อนาที ซึ่งเป็นสถานะที่ให้คอมโพสิตที่มีความทนต่อแรงดึงสูงสุด เมื่อเพิ่มปริมาณของเยื่อเคฟลาร์พบว่า ค่ามอดูลัสมีค่าเพิ่มขึ้น แต่ค่าความทนต่อแรงดึงที่จุดขาด และค่าการยืดตัวที่จุดขาดมีค่าลดลง เมื่อศึกษาสมบัติเชิงกลของคอมโพสิตของเส้นใยที่ผ่านการทำปฏิกิริยา N-alkylation ที่ผิว เปรียบเทียบกับคอมโพสิตของเส้นใยที่ไม่ผ่านกระบวนการทางเคมี พบว่าค่ามอดูลัสลดลงเล็กน้อย ค่าความทนต่อแรงดึงที่จุดขาดมีค่าเพิ่มขึ้น ส่วนค่าการยืดตัวที่จุดขาดมีค่าไม่แตกต่างกันมากนัก เมื่อเปรียบเทียบสมบัติเชิงกลระหว่างคอมโพสิตของเส้นใยเคฟลาร์ชนิด pulp และ short fibre พบว่า คอมโพสิตของเส้นใยชนิด pulp จะมีสมบัติเชิงกลที่ดีกว่า

ส่วนที่สองเป็นการศึกษาการเสริมแรง Santoprene เทอร์โมพลาสติก อีลาสโตเมอร์ โดยใช้เยื่อเคฟลาร์ โดยนำเส้นใยไปทำปฏิกิริยาไฮโดรไลซิสด้วยเบสเพื่อเพิ่มจำนวนหมู่ที่ไวต่อการทำปฏิกิริยาบนผิวของเส้นใย ซึ่งได้ทำการศึกษาผลของการเกิดปฏิกิริยาไฮโดรไลซิสบนผิวของเส้นใย โดยใช้อินฟราเรดสเปกโตรสโกปีและกล้องจุลทรรศน์อิเล็กตรอน หลังจากทำปฏิกิริยาที่ผิวของเส้นใย พบว่าไม่มีการเปลี่ยนแปลงที่ผิวมากนัก การศึกษาสถานะที่เหมาะสมที่สุดในการเตรียมคอมโพสิตระหว่างเยื่อเคฟลาร์และ Santoprene ด้วยเครื่องผสมระบบปิด พบว่า ที่อุณหภูมิ 175 องศาเซลเซียส และความเร็วโรเตอร์ 90 รอบต่อนาที เป็นสถานะที่ให้คอมโพสิตที่มีความทนต่อแรงดึงสูงสุด เมื่อเพิ่มปริมาณของเยื่อเคฟลาร์ พบว่า ค่ามอดูลัส และค่าความทนต่อแรงดึงที่จุดขาดมีค่าเพิ่มขึ้น แต่ค่าการยืดตัวที่จุดขาดมีค่าลดลง การเติมสารช่วยผสมคือ Maleic anhydride grafted polypropylene (MA-g-PP) ลงในคอมโพสิตที่มีเยื่อเคฟลาร์ที่ผ่านการทำปฏิกิริยาไฮโดรไลซิส พบว่า ช่วยทำให้สมบัติเชิงกลดีขึ้น ซึ่งสารช่วยผสมจะทำหน้าที่ได้ดีและทำให้สมบัติเชิงกลของคอมโพสิตดีขึ้นก็ต่อเมื่อใช้ร่วมกับเส้นใยที่ผ่านการทำปฏิกิริยาไฮโดรไลซิสแล้ว